

|                             |                                                                                                                                                                                              |
|-----------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Product Name:</b>        | <b>SUPER-RUSCON</b>                                                                                                                                                                          |
| <b>Reference Number:</b>    | 150-141                                                                                                                                                                                      |
| <b>Coating Type:</b>        | Water-borne rust convertor/passivator.                                                                                                                                                       |
| <b>Typical Uses:</b>        | To passivate <u>residual</u> rust after manual cleaning. Also for use on grit blasted steel with “rust-bloom”.                                                                               |
| <b>Colours Available:</b>   | N/A                                                                                                                                                                                          |
| <b>Surface Preparation:</b> | Remove all <u>loose</u> rust, millscale etc. also any oil or grease. Steelwork exposed in a polluted or marine environment should also be washed with clean water to remove “soluble salts”. |
| <b>Application:</b>         | Apply by brush, roller or spray. A stiff-bristle brush is the preferred method on “pitted” steel to ensure penetration into the <u>rust</u> . Avoid over-application.                        |
| <b>Application Rate:</b>    | Approximately 20m <sup>2</sup> per litre.                                                                                                                                                    |
| <b>Drying Time:</b>         | <b>Firm Dry:</b> 3 hours.<br><b>Overcoat:</b> After 3 hours and <u>within</u> 48 hours.                                                                                                      |
| <b>Shelf Life:</b>          | 2 years in unopened containers, when stored under cover in good storage conditions.                                                                                                          |
| <b>Storage:</b>             | Under cover within temperature range of 5°C to 32°C.<br><b><u>Protect from frost.</u></b>                                                                                                    |
| <b>Clean-up:</b>            | Water.                                                                                                                                                                                       |
| <b>Health and Safety:</b>   | Please see relevant MSDS sheet.                                                                                                                                                              |

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

**Issued:** February 2002

SW/DAE/WHC