

<b>Product Name:</b>	<b>BLACK BITUMEN</b>
<b>Reference Number:</b>	150-396
<b>Coating Type:</b>	Bitumen solution.
<b>Typical Uses:</b>	Protection of steel, concrete, etc. Outstanding water resistance. Suitable for steelwork, pipes, etc.
<b>Colours Available:</b>	Black.
<b>Appearance Of Dried Film:</b>	Sheen finish.
<b>Volume Solids:</b>	50%
<b>Solids Content:</b>	56% +/- 1%
<b>Dry Film Thickness:</b>	<b>Typical:</b> 50 Microns.
<b>Theoretical Coverage:</b>	10m <sup>2</sup> per litre at 50 microns dry film thickness.
<b>Drying Time At 20°C: (Will Vary With Temperature, Air Movement etc.).</b>	<b>Touch Dry:</b> 4 Hours <b>Overcoat:</b> After 16 Hours
<b>Packaging:</b>	5 litre containers.
<b>Shelf Life:</b>	2 years or longer in unopened containers, when stored under cover in good storage conditions.
<b>Storage:</b>	Under cover within temperature range of 5°C to 32°C.
<b>Surface Preparation:</b>	<b><u>Steel</u></b> Thoroughly wire brush to remove all rust, mill-scale, etc. Degrease with Dacrylate Thinner R70 or R1.  A coat of Anti-Corrosive Primer (e.g. Dacrylate Rapidac Primer, ref:13-line) is advisable to prolong the life of the coating.  <b><u>Brickwork, Concrete, Etc</u></b> Remove loose, friable material using stiff bristle brush to leave sound surface.  <b><u>Asbestos, Cement-Based Board, Etc</u></b> Remove loose dirt, dust, etc., using stiff bristle brush.

Continued/

- Application:** Apply by brush, roller or conventional spray.  
Up to 5% of Dacrylate Thinner R70 may be added to achieve optimum spray characteristics.
- Clean-Up:** Dacrylate Thinner R1 or R70.
- Health And Safety:** Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

**Issued:** MAY 2013

MT/DAE/HC