

TECHNICAL PRODUCT DATASHEET

Epidac AC

Epidac AC Primer is a hard, chemical resistant primer for steel. Ideal for use in severe environments, including industrial and chemical plant where quick drying is required. Developed with excellent anti-corrosive properties, **Epidac AC** is also easy to apply.

PRODUCT INFORMATION

Coating type:

2-pack polyamide cured epoxy/zinc phosphate.

Reference Number:

79-LINE

Features and benefits:

- Excellent anti-corrosive properties
- Quick drying 2-pack epoxy
- High build and sag tolerance
- Ease of application
- VOC compliant to EPA PG6/23

Appearance:

Low sheen

Colours available:

Grey Red Oxide
White Buff

TECHNICAL INFORMATION

Theoretical coverage:

8m² per litre at 50 microns dry film thickness

Recommended topcoats:

Dacthane 85 (85-LINE)
Dacfree 581 (81-LINE)
Dacsil 200 (200-LINE)

Sag tolerance:

300 microns wet film thickness

% Volume solids:

40% calculated from laboratory formulation
May vary with colour.

Film thickness:

	Wet film thickness	Dry film thickness
Typical:	125 microns	50 microns
Range:	75-300 microns	30-120 microns

Drying time:

Temp.	Touch dry	Firm dry	Overcoat
5°C	2hrs 30mins	10hrs	When firm-dry, but within 72hrs
10°C	2hrs	8hrs	
15°C	1hr 30mins	6hrs	
20°C	1hr	4hrs	

V.O.C.:

470g/m²/ltr EPA Method 24
356g/m²/kg calculated from formulation to satisfy EU Solvent Emissions Directive
May vary with colour.

Drying time will vary with temperature, air movement, etc. After 72 hours, lightly abrade surface and 'solvent-wipe' before over coating.

SURFACE PREPARATION

Paint preparation before use:

Stir the base component thoroughly, then add the activator to the base in the ratio mentioned below. Mix the activator and base until they become homogenous.

Mixing ratio by volume:

2-parts base to 1-part activator

Surface preparation:

All surfaces to be coated should be clean, dry, and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Abrasive blast to ISO8501-1:2007 SA2.5 standard.

APPLICATION

Application conditions:

This material should preferably be applied at temperatures more than 10°C. Relative humidity should not exceed 90% and in these conditions good ventilation is essential. Substrate temperature should be at least 3°C above the dew point and always above 0°C.

At application temperatures below 10°C, drying and curing times will be significantly extended, and spraying characteristics may be impaired.

Airless spray:

Tip size: 13-15thou (0.33-0.38mm)

Tip pressure: Minimum 2000psi (137bar)

Conventional spray:

Tip size: 55 thou (1.4mm)

Tip pressure: 40-60psi (2.76-4.14bar)

Brush/roller applications:

This product is not suitable to be brushed or rolled.

Thinning:

Dacrylate Thinner R9 may be required when spraying the product to achieve optimum spray characteristics.

Clean-up:

Clean all equipment after use with Dacrylate Thinner R9. Do not allow product to remain in hoses, guns, or spray equipment. All surplus products should be disposed of in accordance with appropriate regional regulations/legislation.

STORAGE AND PACKAGING

Storage:

Under cover within temperature range of 5°C to 32°C. Keep containers dry and tightly sealed to avoid moisture contamination.

Shelf life:

2 years or longer in unopened containers when stored under cover within a temperature range of 5°C to 32°C.

Pot life (at 20°C):

8 hours

Packaging:

5 litre containers

HEALTH AND SAFETY

Please refer to the following data sheets:

79-LINE 20275 Epidac AC Base

79-A133 20247 Epidac AC Activator

All work involving the application and use of this product should be performed in compliance with all relevant national, health, safety & environmental standards, and regulations

ADDITIONAL NOTES

The application and spray information given above is intended as a guide only. As conditions vary from job-to-job, it is the applicators responsibility to ensure all equipment in use has been set up to give the best results.

IMPORTANT INFORMATION

The information supplied in this product datasheet is not intended to be exhaustive. Any person using the product for any other purpose than that specifically recommended in this product datasheet, without first obtaining written confirmation from Dacrylate Technical Services as to the suitability of the product for the intended purpose does so at their own risk. All advice given about the product is correct to the best of our knowledge, however we have no control over the condition of the substrate, preparation or the many factors affecting the use and application of the product. Therefore, unless specifically agreed in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product.

Dacrylate warrants its products to be free from defects in material and workmanship. Dacrylate's obligations and buyer's exclusive remedy relating to the products shall be limited, at Dacrylate's option, to either replace the products not conforming the warranty or the credit of the buyers account in the invoiced amount of the non-conforming product. Any claim under this warranty must be made by the Buyer to Dacrylate in writing within five (5) days of the Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. The Buyer's failure to notify Dacrylate of such non-conformance as required herein shall bar the Buyer from recovery under this warranty.

The information detailed in this datasheet is liable to modification from time-to-time in the light of experience and our programme of product development. Before use, it is the customers responsibility to check with Dacrylate Customer Services, quoting the product reference number and version reference at the bottom of the data sheet, to ensure that they have in their possession the latest issue.

Technical product datasheets are available from our website at www.dacrylate.co.uk, and should be the same as this datasheet. Should there be any discrepancies between this document and the website version, then please contact Dacrylate Customer Services.

© **Dacrylate Paints Ltd. 2020**

Lindley's Lane, Kirkby-in-Ashfield, Nottinghamshire NG17 8AL. Tel.: 01623 753845 Email: enquiries@dacrylate.co.uk

www.dacrylate.co.uk